

Technical Data Sheet



Floor Tile Grout

TA 01

*Wide joint 3-12mm water –
Resistant Interior & Exterior use
BS EN 13888-CGI*



Larsen Floor Grout TA 01 is a high quality, cement based wide joint gout. It is manufactured from a blend of specially selected sands, cement and additives to provide an easy to use water resistant gout ideal for external and internal use.

Larsen Building Products (I) Pvt. Ltd.

Tiles & Stone Adhesive | Grouting | Screeds | Waterproofing | Admixture | Epoxy Flooring

Rajasthan Office : 208, Ganpati Tower, Amrapali Marg, Vaishali Nagar, Jaipur-302 021-Rajasthan
Head Office : A-1, TST Mansion, Tsimshatsuei Kowloon Hong Kong
E-mail : support@neolarsen.com, www.neolarsen.com • C. Care : +91-9982388929

TDS of Floor Tile Grout TA01



PRODUCT INFORMATION	
Form :	Granular
Standard Colour (s) :	White, Grey, Black, Ivory, Brown, Sandstone etc.
Maximum Aggregate Size :	0.6mm
Hazard Information :	Irritant - Consult Safety Datasheet before use
Cleaning :	Clean tools, equipments etc. using warm water. Mechanical means are necessary when the product has set.
Packaging:	1 kg, plastic bags.
Storage Conditions :	Storer in sealed containers in dry conditions, protected from extremes of temperature
Shelf Life :	18 months in unopened manufacture's packaging
APPLICATION INFORMATION	
Water Demand :	300ml /1kg
Application Temperature:	5 °C to + 35°C
Working Time :	1 hour
Joint width :	3-12mm
Light Traffic :	After 12-24 hours
Full Traffic :	After 24-48 hours
PERFORMANCE INFORMATION	
Compressive Strength :	>15 MPa
Flexural Strength :	>2.5 Mpa
Shrinkage :	<3mm / m

Larsen Building Products (I) Pvt. Ltd.

Tiles & Stone Adhesive | Grouting | Screeds | Waterproofing | Admixture | Epoxy Flooring

Rajasthan Office : 208, Ganpati Tower, Amrapali Marg, Vaishali Nagar, Jaipur-302 021-Rajasthan
Head Office : A-1, TST Mansion, Tsimshatsuei Kowloon Hong Kong
E-mail : support@neolarsen.com, www.neolarsen.com • C. Care : +91-9982388929

DIRECTION FOR USE

SUBSTRATE PREPARATION

Ensure the tile adhesive is sufficiently cured prior to commencing grouting. Allow 24 hours when using Larsen TA 01 ready mixed tile adhesives or 2-3 hours when using Larsen Standard fast set. Ensure that the joints are clean and dust free, and are a minimum of 3mm wide and deep.

MIXING

Larsen TA 01 Floor Tile Grout should be added to clean water and mixed to a thick, creamy consistency at approximately 300ml of water per 1 kg of powder. Allow to stand for 3-5 minutes, and then stir again. Do not add further water.

APPLICATION

Apply the grout to the joints with a grouting trowel, squeegee or sponge, ensuring that the joints are completely filled. Compact the grout in the joints and clean off excess with a damp cloth or sponge as the grouting proceeds. Allow the grout to harden sufficiently to prevent removal from the joints when cleaning. This hardening will usually occur within 1-2 hours. In exterior conditions, it is essential to provide protection from all extremes of climate for as long as possible during and after grouting has been completed (a minimum of 72 hours is recommended). Larsen floor Tile Grout will take longer to harden and set at lower temperatures, and should not be used below 5°C.

RESTRICTIONS

All tile surfaces should be checked before starting to ensure colour staining of porous surfaces or scratching of glazed surfaces will occur during grouting. All work should be carried out to current best practice. Floor Tile grout is not suitable for use in areas prone to movement.

Larsen Building Products (I) Pvt. Ltd.

Tiles & Stone Adhesive | Grouting | Screeds | Waterproofing | Admixture | Epoxy Flooring

Rajasthan Office : 208, Ganpati Tower, Amrapali Marg, Vaishali Nagar, Jaipur-302 021-Rajasthan

Head Office : A-1, TST Mansion, Tsimshatsuei Kowloon Hong Kong

E-mail : support@neolarsen.com, www.neolarsen.com • C. Care : +91-9982388929